

MIT Powder Coatings

(616) 350-8549 Date: June 12, 2015

TECHNICAL DATA

Product Number:PESR-400-SG6Product Description:Crimson Red

Physical Properties:

SPECIFIC GRAVITY:	1.47 +05	
GEL TIME @ 400°F:	110-120 sec	
FLEXABILITY:		
IMPACT DIRECT:	160 inch/pour	nds- Pass
IMPACT REVERSE: 160 inch/pounds- Pass		
GLOSS (60°):	80-90	
THICKNESS:	2.0 - 3.0 mils	
PENCIL HARDNESS:	H- 2H	
MEK RESISTANCE (Double-Rubs): 20 - Softens & Recovers		
CONICAL MANDREL:	100% Pass	
ADHESION TEST:		
CROSS HATCH:	100% Pass	
SALT SPRAY:	1,000 hrs. +	
QUV:	1,000 hrs. +	
HUMIDITY:	1,000 hrs. +	
Other Information:		
METHOD:		Electrostatic Spray
VOLTAGE:		70 KVA
CURE CYCLE:		10 min @ 400°F
RECOMMENDED FILM THICKNESS:		2.0 – 3.0 mils
SUBSTRATE:		CRS/Bonderite 1000
CALCULATED COVERAGE (@ 1 mil):		131 sq./ft.
USAGE:		Functional/Decorative Coatings

STORAGE CONDITIONS: Store in cool, dry area (max. 80°F)

The above information is considered to be accurate based on data received from our raw material suppliers. While this information is believed to be reliable, no warranty is issued for the accuracy of this data or for which MIT Powder Coatings assumes legal liability for results to be obtained from the use thereof.