

## **MIT Powder Coatings**

(616) 350-8549 Date: June 12, 2015

## **TECHNICAL DATA**

Product Number:PESP-400-G9Product Description:Purple Wave

## **Physical Properties:**

**SPECIFIC GRAVITY:** 1.50 + -.05GEL TIME @ 400°F: 165 - 175 sec FLEXABILITY: IMPACT DIRECT: 160 inch/pounds- Pass IMPACT REVERSE: 160 inch/pounds- Pass GLOSS (60°): 90 +THICKNESS: 2.0 - 3.0 mils PENCIL HARDNESS: H - 2H MEK RESISTANCE (Double-Rubs): 20 - Softens & Recovers CONICAL MANDREL: 100% Pass ADHESION TEST: **CROSS HATCH:** 100% Pass SALT SPRAY: 1,000 hrs.\* OUV: 1,000 hrs.\* HUMIDITY: 1.000 hrs.\*

\*with proper pretreatment and application

METHOD:	Electrostatic Spray
VOLTAGE:	70 KVA
CURE CYCLE:	10 min @ 400°F
<b>RECOMMENDED FILM THICKNESS:</b>	2.0 – 3.0 mils
SUBSTRATE:	CRS/Bonderite 1000
CALCULATED COVERAGE (@ 1 mil):	128.8 sq./ft.
USAGE:	Functional/Decorative Coatings

STORAGE CONDITIONS: Store in cool, dry area (max. 80°F)

The above information is considered to be accurate based on data received from our raw material suppliers. While this information is believed to be reliable, no warranty is issued for the accuracy of this data or for which MIT Powder Coatings assumes legal liability for results to be obtained from the use thereof.