



MIT Powder Coatings

(616) 350-8549

Date: July 12, 2012

TECHNICAL DATA

Product Number: PESW-500-G9
Product Description: Sky White

Physical Properties:

SPECIFIC GRAVITY:	1.65 +- .05
GEL TIME @ 400°F:	175-185 sec
FLEXIBILITY:	
IMPACT DIRECT:	160 inch/pounds- Pass
IMPACT REVERSE:	160 inch/pounds- Pass
GLOSS (60°):	90 +
THICKNESS:	2.0 – 3.0 mils
PENCIL HARDNESS:	H – 2H
MEK RESISTANCE (Double-Rubs):	20-Softens & Recovers
VOLATILE ORGANICS (VOCs):	< 5%
CONICAL MANDREL:	100% Pass
ADHESION TEST:	
CROSS HATCH:	100% Pass
SALT SPRAY:	1,000 hrs. -
QUV:	1,000 hrs. -

Other Information:

METHOD:	Electrostatic Spray
VOLTAGE:	70 KVA
CURE CYCLE:	10 min @ 400°F
RECOMMENDED FILM THICKNESS:	2.0 – 3.0 mils
SUBSTRATE:	CRS/Bonderite 1000
CALCULATED COVERAGE (@ 1 mil):	117 sq./ft.
USAGE:	Functional/Decorative Coatings

STORAGE CONDITIONS: Store in cool, dry area (max. 80°F)

The above information is considered to be accurate based on data received from our raw material suppliers. While this information is believed to be reliable, no warranty is issued for the accuracy of this data or for which MIT Powder Coatings assumes legal liability for results to be obtained from the use thereof.